

## TECHNICAL SHEET



Article:	<b>B0878 BE-FIT</b>
Norm:	<b>UNI EN ISO 20345:2012</b>
Safety Class:	<b>S1 P SRC</b>
ESD protection for electronic devices	
Footwear height:	<b>Mod. A, H 95 mm (&lt; 113 mm, Ref: EN 20345-5.2.2)</b>
Width:	<b>12</b>
Construction:	<b>STROBEL; PU-TPU SKIN SOLE</b>
Cleaning and maintenance:	Use only soft brushes and water. Do not use substances like alcohol, thinners, gasoline, oil or any other chemicals. Keep the footwear, dry and clean, in a proper place at room temperature.
Suggested fields :	<b>Building, services, light industry, craftsman, automotive, automated lines.</b>

Entire footwear: components				
Component	Description	Value	Norm Requirements	EN 20345
Metal-free	Impact resistance(200 J)			
SLIMCAP toe-cap	<ul style="list-style-type: none"> <li>Free height after impact</li> </ul>	14,0 mm	≥ 14 mm	5.3.2.3
	<ul style="list-style-type: none"> <li>Compression resistance (15 kN)</li> <li>Free height after compression</li> </ul>	15,0 mm	≥ 14 mm	5.3.2.4
Sole (SRC)	Slip resistance			
	<ul style="list-style-type: none"> <li>SRA – Sole (entire sole)</li> </ul>	0,45	≥ 0,32	5.3.5.4
	<ul style="list-style-type: none"> <li>SRA – Heel (Angle of 7°)</li> </ul>	0,39	≥ 0,28	5.3.5.4
	<ul style="list-style-type: none"> <li>SRB – Sole (entire sole)</li> </ul>	0,32	≥ 0,18	5.3.5.4
	<ul style="list-style-type: none"> <li>SRB – Heel (Angle of 7°)</li> </ul>	0,28	≥ 0,13	5.3.5.4
Fresh'n Flex (P)	Puncture resistance	No perforation	≥ 1100 N	6.2.1.1.2
Footbed (A)	Antistatic properties			
	<ul style="list-style-type: none"> <li>Electrical resistance</li> </ul>	dry 5,7 x 10 <sup>8</sup> Ω	≥ 10 <sup>5</sup> Ω , ≤ 10 <sup>9</sup> Ω	6.2.2.2
		humid 2,4 x 10 <sup>8</sup> Ω	≥ 10 <sup>5</sup> Ω , ≤ 10 <sup>9</sup> Ω	6.2.2.2
Sole/Upper	Thermal insulation			
Heat (HI)	Insole temperature increase	N/A	≤ 22°C	6.2.3.1
Cold (CI)	Insole temperature release	N/A	≤ 10°C	6.2.3.2
Heel (E)	Shock-absorption in the heel region	38 J	≥ 20 J	6.2.4
(WR)	Water resistance (Water absorption)	N/A	≤ 3 cm <sup>2</sup>	6.2.5
(M)	Metatarsal protection	N/A	≥ 40 mm	6.2.6

<b>Upper</b>				
<b>Component</b>	<b>Description</b>	<b>Value</b>	<b>Norm Requirements</b>	<b>EN 20345</b>
Microfibre	Tear resistance	80 N	≥ 60 N	5.4.3
	Traction resistance	N/A	≥ 15 N/mm <sup>2</sup>	5.4.4
	Water steam permeability	2,8 mg/cm <sup>2</sup> h	≥ 0,8 mg/cm <sup>2</sup> h	5.4.6
	pH value	N/A	≥ 3,2	5.4.7
	Chromium VI	Non detected	Non detectable	5.4.9
	Water passed	N/A	≤ 0,2 g	6.3
	Water absorption	N/A	≤ 30%	6.3
Hi-tech fabric	Tear resistance	60 N	≥ 60 N	5.4.3
	Traction resistance	N/A	≥ 15 N/mm <sup>2</sup>	5.4.4
	Water steam permeability	9,6 mg/cm <sup>2</sup> h	≥ 0,8 mg/cm <sup>2</sup> h	5.4.6
	pH value	N/A	≥ 3,2	5.4.7
	Chromium VI	N/A	Non detectable	5.4.9
	Water passed	N/A	≤ 0,2 g	6.3
	Water absorption	N/A	≤ 30%	6.3

<b>Lining</b>				
<b>Component</b>	<b>Description</b>	<b>Value</b>	<b>Norm Requirements</b>	<b>EN 20345</b>
3D hi-tech Fabric	Tear resistance	30 N	≥ 15 N	5.5.1
	Abrasion resistance	<ul style="list-style-type: none"> <li>Dry : the surface shows no holes</li> </ul>	No holes till 51.200 cycles	5.5.2
		<ul style="list-style-type: none"> <li>humid: the surface shows no holes</li> </ul>	No holes till 25.600 cycles	5.5.2
	Water steam release	7,2 mg/cm <sup>2</sup> h	≥ 2,0 mg/cm <sup>2</sup> h	5.5.3
	pH value	N/A	Non detectable	5.5.4
	Chromium VI	N/A	Non detectable	5.5.5

<b>Insole</b>				
<b>Component</b>	<b>Description</b>	<b>Value</b>	<b>Norm Requirements</b>	<b>EN 20345</b>
Fresh'nFlex	Thickness	3,5 mm	≥ 2,0 mm	5.7.1
	pH value	N/A	Non detectable	5.7.2
	Water absorption	98mg/cm <sup>2</sup>	≥ 70 mg/cm <sup>2</sup>	5.7.3
	Water release	92%	≥ 80 %	5.7.3
	Abrasion resistance (after 400 cycles)	No damage	Damage ≤ to norms reference	5.7.4.1
	Chromium VI	N/A	Non detectable	5.7.5

<b>Removable footbed</b>				
<b>Component</b>	<b>Description</b>	<b>Value</b>	<b>Norm Requirements</b>	<b>EN 20345</b>
Anatomical, breathable, textile and expanded polymeric material	Thickness	3,5±0,5 mm	N/A	5.7.1
	pH value	N/A	Non detectable	5.7.2
	Water absorption	Permeable	Permeable or ≥ 70mg/cm <sup>2</sup>	5.7.3
	Water release	Permeable	Permeable or ≥ 80%	5.7.3
	Abrasion resistance	No damage	Dry No holes till 25600 cycles Humid no holes till 12800 cycles	5.7.4.2
	Chromium VI	N/A	Non detectable	5.7.5

Sole				
Component	Description	Value	Norm Requirements	EN 20345
	Sole thickness without profile	7,1 mm	≥ 4 mm	5.8.1.1
	Profile height	4,1 mm	≥ 2,5mm	5.8.1.3
	Tear resistance	6,9 kN/m	≥ 5 kN/m	5.8.2
PU Midsole	Abrasion resistance			
	• relative volume loss	72 mm <sup>3</sup>	≤ 250 mm <sup>3</sup>	5.8.3
Outsole	Flexion resistance			
TPU SKIN: (TPU high density)	• Notches increase after 30.000 cycles	1,0 mm	≤ 4 mm	5.8.4
	• Hydrolysis	2 mm	≤ 6 mm	5.8.5
	Notches increase after 150.00 cycles	3,8 N/mm <sup>(*)</sup>	≥ 4 N/mm; (*) ≥ 3 N/mm with sole ripping	5.8.6
	(HRO) Contact heat resistance (300°C)	N/A	No damage (melting, breaking)	6.4.1
	(FO) Fuel resistance (volume changes)	0,8 %	≤ 12%	6.4.2

Date: 09/06/2015

Issued by: Resp. Techn. Eng. Cataldo De Luca

Signature:

